

# HDPE

HDPE for PE-RT

## ▶ XRT70K

### ● Description

HDPE XRT70K is a high performance hexene-based polyethylene primarily intended for hot & cold water pipe as well as demanding industrial pipe applications.

### ● Characteristics

- ▶ PE-RT Type II classification
- ▶ superior resistance to slow crack growth coupled with a MRS of 10 MPa, ensuring safe and durable pipe systems operation
- ▶ broad bimodal molecular weight distribution offering outstanding processing properties from small bore pipes to larger diameter pipes extrusion, for both mono- and multi-layer applications
- ▶ optimized formulation of additives providing excellent long-term stability in service at elevated temperatures

### ● Physical Properties

Properties	Test Method	Units	XRT70K
Melt Index (190°C/5kg)	ISO 1133	g/10min	0.7
Density	ISO 1183	g/cm <sup>3</sup>	0.947
Oxygen Induction Time (210°C)	ISO 11357-6	min	>40
Thermal Conductivity (60°C)	Hanwha Total	W/m <sup>°K</sup>	0.35
Coefficient of Linear Thermal Expansion (40°C)	Hanwha Total	m/m <sup>°K</sup>	1.7E-4
Tensile Modulus	ISO 527	MPa	850
Tensile Strength at Yield	ISO 527	MPa	23
Tensile Elongation at Break	ISO 527	%	≥350
Flexural Modulus	ISO 178	MPa	750
FNCT (Arkopal, 80°C, 4.0MPa)	ISO 16770	hr	≥2000
Charpy Impact Strength (0°C)	ISO 868	kJ/m <sup>2</sup>	20

\*These are typical property values and are not to be construed as specifications.

## ● **Contacts**

---

### ▶ **Polymer Application Tech. Team**

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do,  
Korea, 31900

TEL : 82-41-660-6190      FAX : 82-41-660-6189

### ***Disclaimer***

---

*This document is copyright of Hanwha Total petrochemical Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.*