

HANWHA

Linear Low Density Polyethylene

3120

Blown Film Grade

MELT INDEX 1.0
DENSITY 0.920

HANWHA LLDPE 3120 is manufactured by Unipol process and designed for general purpose and agricultural film . LLDPE 3120 has well balanced property of mechanical property, processability and optical property

This product complies with U.S. FDA regulation 21 CFR 177.1520 (c) 3.1.a.

▣ Outstanding Properties

Mechanical Property
Optical Property
Processability

▣ Processing Conditions

Melt Temperature : 150 ~ 190 °C
Blow-up Ratio : 2 ~ 3
Optimum Gage Range : 0.03 ~ 0.1 mm

▣ Additives

Antioxidant, Slip agent, Anti-blocking agent

▣ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	1.0
Density	g/cc	ASTM D1505	0.920
Vicat Softening Point	°C	ASTM D1525	103
Melting Point	°C	HCC Method	122
Tensile Strength at Break	kg/cm ²	ASTM D638	220
Elongation at Break	%	ASTM D638	900
Brittleness Temperature, F ₀	°C	ASTM D746	< -76
Film Properties	Unit	Test Method	Value
Film Thickness	mm	HCC Method	0.03
Tensile Strength at Break	kg/cm ²	ASTM D882	MD 420
			TD 380
Elongation at Break	%	ASTM D882	MD 650
			TD 750
Tensile Tear Strength	Kg/cm	ASTM D1004	MD 120
			TD 125
Dart Impact Strength	g	ASTM D1709	140
Haze	%	ASTM D1003	10.0

1. These are typical properties : not to be construed as specification.
2. The value for this property is dependent on part geometry and fabrication conditions.

