



HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE

High Density Polyethylene

HD5208 FLX

Technical support:

Sasol Chemicals
North America LLC
12120 Wickchester Lane
Houston, TX 77079

Email:
PolymersTechnical@us.sasol.com

Sales office:

Sasol Chemicals
North America LLC
12120 Wickchester Lane
Houston, TX 77079
Telephone: (281) 588 3000
Email:
PolymersSales@us.sasol.com

Date of issue February 01, 2019

www.sasol.com

High Load Melt Index: 9.0 g/10min

Density: 0.952 g/cm³

Features

- High molecular weight hexene copolymer HDPE with a bimodal molecular weight distribution.
- Excellent draw-down for thin films.
- Bubble stability for high rates.
- Good balance of stiffness and toughness.

Potential Applications

- Thin films for trash can liners, t-shirt bags, merchandise bags, produce bags and roll stock.
- Thick film for multi use applications.

Additives

- Antioxidant

Typical properties (not to be construed as specifications)		Value (English)	Value (SI)	Method
Resin Properties	Melt Index (190°C/2.16kg)	0.057 g/10min	0.057 g/10min	ASTM D1238
	High Load Melt Index (190°C/21.6 kg load)	9.0 g/10min	9.0 g/10min	ASTM D1238
	Density	0.952 g/cm ³	0.952 g/cm ³	ASTM D4883
Physical Properties	Tensile Strength at Yield MD	4500 psi	31 MPa	ASTM D882
	Tensile Strength at Yield TD	3900 psi	27 MPa	ASTM D882
	Tensile Strength at Break MD	11000 psi	76 MPa	ASTM D882
	Tensile Strength at Break TD	7000 psi	48 MPa	ASTM D882
	Elongation at Break MD	>250 %	>250 %	ASTM D882
	Elongation at Break TD	>350 %	>350 %	ASTM D882
	1% Secant Modulus MD	112000 psi	772 MPa	ASTM D882
	1% Secant Modulus TD	139000 psi	958 MPa	ASTM D882
	Dart Drop Impact	350 g	350 g	ASTM D1709
	Elmendorf Tear MD	37 g	37 g	ASTM 1922
Elmendorf Tear TD	83 g	83 g	ASTM 1922	

HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours.

Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage.

Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. be equipped with adequate filters
2. is operated and maintained in such a manner to ensure no leaks develop
3. that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

This publication contains information provided in good faith and is indicative, based on Sasol's current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased from Sasol Chemicals are subject to the terms and conditions as set out in the contract, order confirmation and/or bill of lading.